Effect of Temperature on the Structural and Magnetic Properties of CuFe_2O_4 Nano Particle Prepared by Chemical Co-Precipitation Method

Sakia Shabnam Kader, Deba Prasad Paul, and Shaikh Manjura Hoque

Abstract—The behaviors of the CuFe_2O_4 nano particle prepared by chemical co-precipitation have been studied. The XRD result of the as dried and samples calcined at different sintering temperature has shown that the single phase has been observed in the as dried condition and there is no observation of extra peak. The grain size has been obtained from Scherrer's formula and found as 4nm to 56nm for the CuFe_2O_4 nano particle sample with the systematic variation of sintering temperature. Nano particle has been characterized to understand the magnetic properties from the observation of hysteresis loops. The initial permeability varies with sintering temperature due to the variation in kinetics of diffusion which depends on the particle size of the starting material. The Curie temperature has been measured from the result of temperature dependent initial permeability.

Index Terms— CuFe_2O_4 , curie temperature, grain size, initial permeability.

I. INTRODUCTION

Magnetic nano particles show remarkable new phenomena such as super para magnetism, high field irreversibility, high saturation field, extra anisotropy contributions. These phenomena arise from finite size and surface effects that dominate the magnetic behavior of individual nanoparticles [1]. Ferrite nano particles are most explored nano particle which can be manipulated using magnetic field. The outstanding property of ferrites which make them suitable for many applications is their high electrical resistivity compared to those metals [2]. Copper ferrite (CuFe_2O_4) is basically an inverse spinel ferrite in which the tetrahedral (A) sites are occupied by ferric ions, and octahedral (B) sites by ferric and copper ions. The magnetic properties and the cation distribution are found to be different in nano crystalline spinel ferrites, when compared to the bulk counterpart [3]. The saturation magnetization for the nanocrystalline ferrites in general is found to be lower compared to their bulk value, which is attributed to surface spin effects. In some cases an enhancement in the saturation magnetization is observed due to the change in cation distributions which depends on the crystal field stabilization energy of the cations. Apart

from grain size, the cation distribution, which depends on the synthesis condition, is found to play a major role in the observe changes in their magnetic properties [4]. According to the synthesis of the nano materials, various structural features have found which depend on the manner, such as surface pores, grain boundary junctions and other crystal lattice defects. Some examples are lowered melting temperatures, improved wear resistance of nano structured ceramics, increased strength of metals and transformation of magnetic state from ferromagnetic to paramagnetic or super paramagnetic state as a function of size. Further, nanotechnology was also expanded extensively to other fields of interest due to the novel properties of nanomaterials discovered and to be discovered. For example, nanowires can be potentially used in nanophotonics, laser, nanoelectronics, solar cells, resonators and high sensitivity sensors. Nanoparticles can be potentially used in catalysts, functional coatings, nanoelectronics, energy storage, drug delivery and biomedicines [5].

II. EXPERIMENTAL DETAILS

The fine particles of CuFe_2O_4 have produced by a standard co-precipitation technique. The starting materials were $\text{Cu}(\text{NO}_3)_2 \cdot 3\text{H}_2\text{O}$ [copper nitrate tri hydrate], $\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ [Iron nitrate nano hydrate] and sodium hydroxide (NaOH). Two separate solutions, one a solution of copper nitrate in de ionized water and the other contains a solution of Iron nitrate in de ionized water were prepared. The former solution was added drop wise into the later. Then the two solutions were mixed the solution of sodium hydroxide. Then the mixed solution was stirred by magnetic stirring apparatus (300 rpm) at temperature 200 °C. When the reaction was complete, the resultant deep blue solution was filtered and washed with de ionized water for 10 times and was dried at the temperature above 100 °C for 36 hours, then calcined at various temperatures. Following this process, six batch samples were prepared by varying different parameters such as stirring temperature, pH and drying temperature. The X-Ray diffraction (XRD) of CuFe_2O_4 nano particles has shown that the grain size is 4nm to about 56nm according to the systematic variation of the calcinations temperature.

III. RESULTS AND DISCUSSION

X-ray diffraction pattern of CuFe_2O_4 samples calcined at different temperature have been presented in Fig. 1.

Manuscript received May 19, 2013; revised July 27, 2013.

Sakia Shabnam Kader is with the Department of Natural Sciences, Daffodil International University, Dhaka, Bangladesh (e-mail: ssk28@daffodilvarsity.edu.bd).

Deba Prasad Paul is with the Department of Physics, University of Chittagong, Chittagong, Bangladesh (e-mail: dprasad69@yahoo.com).

Shaikh Manjura Hoque is with Bangladesh Atomic Energy Centre, Dhaka, Bangladesh (e-mail: manjura_hoque@yahoo.com).

In the as-cast condition, single phase CuFe_2O_4 has formed with no extra peak. At the calcinations temperature of 600°C , slight change in the XRD pattern has found maintaining the same structure. At 800°C fully crystallized CuFe_2O_4 has formed with all peaks matches with the standard patterns. The peak broadening shows that, the CuFe_2O_4 nano particle has formed. The peak width decreases with the increase in calcinations temperature which reflects the coarsening of particles. The size of the nano particles have been determined by using Scherrer's formula from the FWHM of 311 peaks. The grain size has obtained from 4nm to 56 nm for the CuFe_2O_4 nano particle sample with the systematic variation of sintering temperature which is shown in Fig. 2.

Fig. 1. X-Ray diffraction pattern of CuFe_2O_4 samples calcined at different temperature.

Fig. 2. Variation of grain size with sintering temperature.

The grain size increases very rapidly from 200°C - 800°C with increase in the sintering temperature but from 800°C - 900°C , the grain size suddenly drops and then for the sintering temperature 900°C - 1200°C , the size again increases very sharply.

By using vibrating sample magnetometer, the CuFe_2O_4 nano particle has been characterized to understand the magnetic properties.

In Fig. 3, the hysteresis loop for the sintering temperatures 900°C , 1000°C , 1100°C and 1200°C have been presented.

The hysteresis loop contains the soft ferrimagnetic nature of synthesized CuFe_2O_4 . The difference in the value of the

saturation magnetization can be explained in the light of cation distribution. Any change in the concentration and nature of the ions in A-site and B-sites should cause resultant magnetization to be different. The decrease in M_s Value implies that outside a core of ordered moments, those in the surface layer are in a state of a frozen disorder. With the reduction of particle size, more atoms retains on the surface which are not exchange coupled. As a result, the value of magnetization decreases. The effect is more prominent when the particle sizes are very small. On the other hand, the saturation magnetization increases with the increase of particle size since core of the ordered moment's predominant.

Fig. 3. Hysteresis loop for CuFe_2O_4 at sintering temperatures 900°C , 1000°C , 1100°C , 1200°C .

Fig. 4. Frequency (f) dependence of real part of the initial permeability (μ').

Fig. 4. represents the real part of initial permeability as a function of frequency for the CuFe_2O_4 nano particle sample at various sintering temperature (800°C , 900°C , 1000°C , 1100°C , 1200°C). From the fig, it is observed that, μ' is fairly constant up to a certain high frequency and drops rapidly to a very low value at higher frequency. The real part of μ' describes the stored energy expressing the component of magnetic induction in phase with the

alternating magnetic field. The Permeability is directly proportional to the micro structural features. i.e, grain size. The multi domain grains are obtained by increasing the grain size induces in higher permeability due to the domain wall contribution. The Fig also shows that, due to the act of interfering of small grain size with wall motion, the permeability decreases with increasing the stability region of μ' . That is, the stability is maximum at the value of lower permeability. Fig. 5 represents the imaginary part of the initial permeability (μ'') over the frequency range from 1 kHz to 10 kHz for the CuFe_2O_4 sample. The fig shows the curve with a large tail towards the high frequency at which the loss components are lowered. It occurs due to the inhibition of the domain wall motion and the variation of magnetization with the alternating magnetic field. As a result, the value of μ'' decreases rapidly at the low frequency region and becomes almost constant.

Fig. 5. Frequency (f) dependence of the imaginary part of the initial permeability (μ'').

Fig. 6. Temperature dependence of the real part initial permeability (μ').

In Fig 6, the temperature dependence of the real part of the initial permeability has been presented for the CuFe_2O_4 nano particle sample for different sintering temperatures. The magnitude of the initial permeability is proportional to

the square of the saturation magnetization and inversely proportional to the magnetic anisotropy energy.

According to the Hopkinson effect, permeability increases with temperature and shows a maximum just below the Curie point. Near the Curie point, the value of the anisotropy energy almost negligible and the complete disorder take place. At T_c , the sharp falling of μ .

Fig. 7 shows the sintering temperature dependence Curie temperature. In order to find the result, $d\mu/dT$ vs. T has been plotted for different sintering temperatures. The point at which the highest slope change has observed is known as the Curie point and from this point, at low sintering temperature the grain size is very small and the magnetic coupling will be weaker because of the lower coordination of the particles. The magnetic coupling will be stronger with the increase in the sintering temperature. This phenomenon has been reflected in the increment of the Curie temperature. Further increase in the sintering temperature, Curie temperature decreases which have occurred due to the predominance of the effect of the change in cation distribution over the finite size effect on Curie temperature.

Fig. 7. Sintering temperature (T_s) dependence Curie temperature (T_c).

IV. CONCLUSION

The present research work contains the investigative information about the nano magnetic materials including the area of synthesis and characterization of CuFe_2O_4 nano particle. The effect of temperature has been observed in the variation of the structural and magnetic properties. From all the discussed behavior, it can be said that, the properties of materials with nanometer dimensions are significantly different from those of atoms and bulks materials. This is mainly due to the nanometer size of the materials which render them: I) large fraction of surface atoms; II) high surface energy; III) spatial confinement; IV) reduced imperfections, which do not exist in the corresponding bulk materials. The technological and pharmaceutical applications can be taken up as future study for the ferrite nano particle. The research will lead the increasing need of development of ferrite gas sensors for industrial purposes. Pharmaceutical sciences have been using nano particles to reduce toxicity and side effects of drugs. A conceptual

understanding of biological responses to nano materials is needed to develop and apply safe nano materials in drug delivery in the future.

REFERENCES

- [1] X. Batlle and A. Labarta, *J. Phys. D: Apply. Phys.*, vol. 35, pp. R15, 2002.
- [2] C. Kittel, *Introduction to Solid State Physics*, 7th ed., John Wiley and Sons, NY, pp. 17-462.
- [3] B. D. Cullity and C. D. Graham, *Introduction to Magnetic Materials*, Addison-Wesley Publishing, 1972, Com181.
- [4] C. Doroftei, N. Rezlescu *et al.*, *Microstructure and Humidity Properties of $MgFe_2O_4$ Ferrite with Sn and Mo Substitutions prepared by selfcombustion method*.
- [5] R. A. Andrievski, *Journal of Nanoparticle Research* 5, pp. 415, 2003.

Sakia Shabnam Kader is serving as a lecturer in Daffodil International University, Dhaka. She completed her B.Sc. and M.S. in Physics from University of Chittagong. She has strong background in solid state physics and material science. She has research interests in nano magnetic materials, ferrite materials & its bio medical applications. She has worked with nano magnetic materials to provide

services to facilitate quality control and quality assurance of industrial products.

Deba Prasad Paul is serving as a professor in the department of physics in University of Chittagong. He completed his Ph.D. in solid state physics. He has strong background in solid state physics, renewable energy & material science.

Shaikh Manjura Hoque is serving as a principal scientific officer in Bangladesh Atomic Energy Commission, Dhaka. She did her Ph.D. in material Science and Metallurgy. She has continued her research in the field of advanced materials development such as, nanostructure/amorphous materials, magnetic materials, ferrite nano materials, oxide materials, binary alloys, dielectric materials.